

DYNAMIC UV INK DUCT GLOSS

DESCRIPTION OF THE PRODUCT

Modified Acrylate UV glossy coating used in the ink duct

TYPICAL PHYSICAL PROPERTIES

TACK VALUE : 9 ± 1 (400 rpm/30°C, 1 Minutes)

FLOW : $14 \text{ cm} \pm 1$ (On 60° glass wall, 5 Minutes)

DRYING / CURING SPEED

UV CURING POWER : With 1 UV lamp of 80-200 W/cm

CURED FILM APPEARANCE : Gloss Transparent

FIELD OF APPLICATION

METHOD OF APPLICATION : UV Offset System

RUB RESISTENCE : Good

SCRATCH RESISTENCE : Good

SUBSTRATE : BOPP, Absorbent and Non-Absorbent board and Paper board

NOTE

Any excessive inks left in the ink tray should be discard of to avoid any contamination to inks in the containers.

STORAGE

Shelf life is 8 months if kept at 20-27 ° C in a well ventilated area and in a tightly closed containers. Product should not be stored in direct sunlight or any other strong light sources.

SAFETY

Avoid direct contact with skin, eyes and mucous membranes.

Wash with detergent when finish the work.



LINE OA